7. (Amended.) A method according to claim 6, wherein the amount of waste magazines constitutes at least 10% by weight of the total amount of wastepaper.

a1

8. (Amended.) A method according to claim 7, wherein the wastepaper consists essentially of waste magazines.

9. (Amended.) A method according to claim 1, wherein the wastepaper comprises old newspapers and waste magazines.

10. (Amended.) A method according to claim 9, wherein the wastepaper comprises 1-60% by weight of waste magazines and 40-99% by weight of old newspapers.

a2

12. (Amended.) A method according to claim 1, wherein the pulping with the deinking agent is carried out at a temperature from 25 to 75°C.

13. (Amended.) A method according to claim 1, wherein the fatty acid ester is a methyl ester, an ethyl ester, a *n*-propyl ester, an isopropyl ester, a *n*-butyl ester, an isobutyl ester, a *sec*-butyl ester, a *tert*-butyl ester, a monoglyceride, a diglyceride or a triglyceride of a C_6-C_{22} fatty acid, the C_6-C_{22} fatty acid being optionally substituted with one or more hydroxy, ethoxy, *n*-propoxy and/or isopropoxy groups.

14. (Amended.) A method according to claim 1, wherein the fatty acid ester is a C_6-C_{22} fatty acid, which has been alkoxylated with ethylene oxide, propylene oxide, or a combination thereof.

a3

19. (Amended.) A method according to claim 14, wherein the fatty acid ester is a triglyceride.

a4

21. (Amended.) A method according to claim 1, wherein the pulping step is carried out in the presence of a starch degrading enzyme.

a5

23. (Amended.) A method according to claim 1, wherein the pulping step is carried out in the presence of a cellulase.

a6

26. (Amended.) A method according to claim 1, wherein the lipase is added in an amount corresponding to 0.001 – 0.15% by weight of the dry pulp.

27. (Amended.) A method according to claim 1, wherein the fatty acid ester is added in an amount corresponding to 0.025 - 1% by weight of the dry pulp.